

Silicone-based soft denture liner**SOFRELINER TOUGH M Medium**

REF SR02

ENGLISH

Carefully read all of these instructions before using SOFRELINER TOUGH M.

■ PRODUCT DESCRIPTION AND GENERAL INFORMATION

1. SOFRELINER TOUGH M is an addition-cured silicone chairside soft lining material for removable dentures. SOFRELINER TOUGH M conforms to ISO 10139-2 "Soft lining materials for removable dentures Part 2: Materials for long-term use".
2. SOFRELINER TOUGH M Kit contains PASTE, PRIMER and other accessories such as mixing tips, drip nozzle, drip cup, brushes, SHAPE ADJUSTMENT POINT (White), FINISHING POINT (Brown).
3. PRIMER is used solely for bonding to the acrylic surfaces. It cannot be used to bond nylon, metal and silicone surfaces. PASTE is dispensed in automix cartridge delivery system. The material sets in 5 minute intraorally or 20 minutes at room temperature (23°C / 73.4°F) and has no odor or taste.

■ INDICATIONS

1. Pain caused by sharp ridges of alveolar bone and mucous atrophy.
2. Poor retention caused by extreme ridge atrophy.
3. Major undercut or maxillary / mandibular tori.
4. Retention of overdentures before the final attachment is placed.

■ CONTRAINDICATIONS

SOFRELINER TOUGH M is contraindicated in patients allergic to or hypersensitive to silicone and platinum compounds and should NOT be used on such patients.

■ PRECAUTIONS

1. SOFRELINER TOUGH M is designed for sale and use by licensed dental care professionals only. It is not designed for sale nor is it suitable for use by non-dental care professionals.
2. Use SOFRELINER TOUGH M only as instructed herein. DO NOT use SOFRELINER TOUGH M for any application other than those noted in these instructions.
3. DO NOT use SOFRELINER TOUGH M if the safety seal is broken or if it appears the contents have been tampered with.
4. PRIMER contains ethylacetate, which is a highly flammable and volatile solvent. Do not expose the PRIMER to open flame. Use in a ventilated room during use and close the cap tightly after use.
5. If patient experiences an allergic reaction or sensitivity to SOFRELINER TOUGH M, such as a dermatitis outbreak, remove the prosthesis and discontinue its use immediately.
6. Wear non-latex examination gloves at all times while using SOFRELINER TOUGH M to avoid the possibility of allergic reactions. Latex gloves may also inhibit the setting of SOFRELINER TOUGH M. If SOFRELINER TOUGH M PRIMER comes in contact with the examination gloves, immediately dispose of the examination gloves and wash hands thoroughly with water.
7. Avoid contact with eyes. In case of contact with eyes, thoroughly flush eyes with water, and immediately contact a physician.
8. Avoid contact of unset chemical with skin. In case of contact with skin, clean affected area with rubbing alcohol, then thoroughly flush with water.
9. Avoid contact of unset materials with clothing. In case of contact with clothing, do not wipe the material. Allow it to set and then peel it off.
10. DO NOT allow excess materials to flow down the patient's trachea or esophagus. Aspirated or ingested SOFRELINER TOUGH M PASTE can cause asphyxiation or other injury. Immediately remove any excess lining material from the palatal area to avoid material flowing down the patient's throat. SOFRELINER TOUGH M is not radiopaque, and radiographs will not detect aspirated or ingested material. In case of an elderly patient whose reflex ability is compromised, set the chair in an upright position and instruct the patient to breathe through the nose in order to prevent the material from entering the airway.

11. DO NOT mix SOFRELINER TOUGH M with any materials not noted in these instructions.

12. After using SOFRELINER TOUGH M cartridge, the mixing tip must be replaced with the cartridge cap that comes with the cartridge at the time of purchase. Wipe off the excess paste on the tip of cartridge with a clean cloth or tissue each time before using a new mixing tip or replacing the cartridge cap.

13. Always clean the spatula, brushes and cups with alcohol after each use to avoid cross contamination.

14. Instruct patients in accordance with the PATIENT PRECAUTIONS contained in the last section of these instructions.

15. To avoid inhaling dust while finishing, always wear a mask recommended by federal and/or local regulations.

16. Read and follow the manufacturers' instructions for all products mentioned in this instruction manual that are not included in this kit.

17. As much as possible, avoid contact SOFRELINER TOUGH M with oral mucous membrane other than the region to be lined. Instruct patients to rinse their mouth with adequate amount of water after the treatment.

18. Do not place the PRIMER in direct contact with plastic materials, contact may dissolve some types of plastic.

■ NOTES FOR USE

1. In the case of a poor fitting denture, first line the denture with an acrylic material, such as TOKUYAMA REBASE II, chairside hard denture lining material, or any other laboratory/indirect procedure to improve the fit.
2. In the case of an old worn denture, the surface to be lined should be first lined with new acrylic material since the materials absorbed in the old worn resin such as oil or water lowers the adhesion of SOFRELINER TOUGH M.
3. If the SOFRELINER TOUGH M PRIMER becomes thick due to volatilization, do not use it as the adhesive strength may be reduced.

4. Regarding the brush for the primer, wipe off the tip with alcohol-soaked cotton swab or gauze after each use. Contaminated brush can lower the adhesion of SOFRELINER TOUGH M.

5. Do not mix pastes by hand, doing so may cause air bubbles to be incorporated into the paste, which could result in deterioration, staining and unpleasant odors.

6. Avoid contact SOFRELINER TOUGH M with the materials below, as they may inhibit the setting of SOFRELINER TOUGH M:

Silicone-based impression materials, eugenol containing materials, polysulfide rubber impression materials, natural rubber gloves, other manufacturer's soft lining materials and uncured acrylic resins.

7. The material sets in 5 minutes intraorally or 20 minutes at room temperature (23°C / 73.4°F). After 24 hours the liner turns slightly firmer. The finishing procedure can be performed immediately after the removal of the newly lined denture from the

mouth or a gypsum model.

8. Soaking the denture in solutions containing heavy bleach may alter the color of SOFRELINER TOUGH M; however, it will not affect its performance.
9. Instruct patient to clean the denture as described in PATIENT PRECAUTIONS.
10. Since silicone-based fit checking material sticks to SOFRELINER TOUGH M, apply Vaseline on the surface prior to use.
11. If there is a fracture in the finished liner, completely remove the liner and repeat the procedure.
12. Refer to following tools for shape adjustment and finishing.

Stages	Tools	Shapes
Trimming	Sharp scalpel	Slightly rounded blade
Shape Adjustment	SHAPE ADJUSTMENT POINT (White)	Round tapered end
Finishing	FINISHING POINT (Brown)	Round tapered end
Relief	DIAMOND ROUND BUR (sold separately)	Round

■ STORAGE

1. Store SOFRELINER TOUGH M at a temperature between 0 – 25 °C (32 – 77 °F).
2. Avoid direct exposure of SOFRELINER TOUGH M to heat, open flame, humidity and sunlight.

3. Do not use SOFRELINER TOUGH M after the indicated date of expiration.
4. DO NOT leave SOFRELINER TOUGH M unnecessarily within the reach of patients and children to avoid being swallowed by mistake.

■ DISPOSAL

1. To dispose of the PASTE, dispense unused paste from the cartridge and allow it to set prior to disposal.
2. The remaining PRIMER liquid should be absorbed in an inert absorbent material such as gauze or cotton, and disposed of in accordance with local regulations.

■ CLINICAL APPLICATION OF SOFRELINER TOUGH M**INTRAORAL LINING METHOD**

In most cases the optimum thickness of SOFRELINER TOUGH M should be 1-2 millimeter. If a thickness of over 2 millimeters is required, the area should first be lined with TOKUYAMA REBASE II, chairside hard denture liner, to obtain sufficient denture base. Excessive removal of denture resin could cause denture to fracture and weaken.

1. Preparation

Check intraoral condition by inspection and palpation. Remove denture from patient's mouth and clean the area to be lined with soap and water. Rinse thoroughly and air-dry the denture surface completely. Grind the tissue side of the denture with a cross cut carbide bur to the proper depth. Bevel the borders of the denture to allow 1 millimeter of material to roll over the borders (See Figure 1). Remove the grinding dust with a dry brush or dry oil-free air.

Note: When the border is placed within the flange of denture base, grind the tissue side of the denture with round bur (for acrylic resin) to the proper depth (See Figure 2).




Figure 1




Figure 2

2. Dispensing the PRIMER

Open the bottle of PRIMER. Attach the drip nozzle to the bottle. Dispense an adequate amount of PRIMER into the drip-cup. Replace the cap, closing the bottle tight immediately after dispensing.

3. Applying the PRIMER

Using the brush for the PRIMER, apply a thin, even coat of PRIMER on the denture surface where SOFRELINER TOUGH M is to be lined. Do not miss any areas where the PRIMER should be applied since this may cause poor adhesion. Then air-dry the surface thoroughly until no visible liquid remains.

7. Dispensing the PASTE

Load the SOFRELINER TOUGH M PASTE cartridge into a dispenser (sold separately).

Open the cartridge cap of PASTE. Attach the mixing tip to the cartridge by aligning the notches, push it onto the cartridge, rotating the mixing tip clockwise 90 degrees.

8. Applying the PASTE

Extrude the mixed paste onto the surface where the PRIMER has been applied. Position the paste both on the mucosal side of denture and stone model.

9. Reattachment

Reattach the denture onto its gypsum stone model and press it with the lining jig. Leave undisturbed for 20 minutes or more at room temperature (23°C / 73.4°F).

Note: If the set material is sticky, soak the denture in warm water at 40°C to 50°C (104°F to 122°F) for 5 minutes with the lining jig.

10. Trimming

Remove the denture from the gypsum model. Carefully trim all excess SOFRELINER TOUGH M material from the border areas with a sharp scalpel (See Figure 3).




Figure 3




Figure 4

9. Finishing

For shaping, use the SHAPE ADJUSTMENT POINT (White), by applying light pressure not to exceed 15,000 rpm allowing the point to move in a small circle. For finishing, use the FINISHING POINT (Brown), by applying light pressure not to exceed 4,000 rpm.

Note: Rotate the SHAPE ADJUSTMENT POINT and the FINISHING POINT from the lined area to the denture area so as not to break the margin region (See Figure 4).

Use DIAMOND ROUND BUR (sold separately) or any suitable bur for relief.

10. Readjustment

Readjust the denture according to the procedure of section 9. If new material is to be added to the lined surface, remove the existing liner from the denture base and replace with a new liner.

11. Removal

Remove a large portion of SOFRELINER TOUGH M material by cutting it off with a sharp instrument. Remove the remaining material by grinding.

Note: SILICONE REMOVER (sold separately) easily removes old silicone denture liner from the acrylic denture base.

■ CLINICAL APPLICATION OF SOFRELINER TOUGH M**LABORATORY LINING METHOD****1. Examination of mouth**

Check intraoral condition by inspection and palpation. Examine the area where needs relief.

2. Examination of the denture

If the denture is worn or old, line the denture first using TOKUYAMA REBASE II, chairside hard denture lining material. The hard lining material should be applied in the appropriate thickness so that when the new material is ground down according to the procedure in step 4, a newly lined layer of hard lining material is left on the denture bearing area, allowing SOFRELINER TOUGH M to adhere to it.

3. Fabrication of a gypsum model

Take an impression with the patient biting on the denture, then pour a stone slurry onto the impression. Make a stone index of the teeth and mount the denture on the index of a lining jig. Relieve the stone model with wax in the region where may cause pain in the mouth. Apply a separating medium on the ridge area of the gypsum model so the lining material will not adhere to it.

4. Preparation

Grind the tissue side of the denture with a cross cut carbide bur to the proper depth. Bevel the borders of the denture to allow 1 millimeter of material to roll over the borders (See Figure 1). Remove the grinding dust with a dry brush or dry oil-free air.

Note: Use of a round bur makes it easy to remove a uniform depth of resin. The diameter of the bur can be used as a guide for depth.

5. Dispensing the PRIMER

Open the bottle of PRIMER. Attach the drip nozzle to the bottle. Dispense an adequate amount of PRIMER into the drip-cup. Replace the cap, closing the bottle tight immediately after dispensing.

6. Applying the PRIMER

Using the brush for the PRIMER, apply a thin, even coat of PRIMER on the denture surface where SOFRELINER TOUGH M is to be lined. Do not miss any areas where the PRIMER should be applied since this may cause poor adhesion. Then air-dry the surface thoroughly until no visible liquid remains.

7. Dispensing the PASTE

Load the SOFRELINER TOUGH M PASTE cartridge into a dispenser (sold separately). Open the cartridge cap of PASTE. Attach the mixing tip to the cartridge by aligning the notches, push it onto the cartridge, rotating the mixing tip clockwise 90 degrees.

8. Applying the PASTE

Extrude the mixed paste onto the surface where the PRIMER has been applied. Position the paste both on the mucosal side of denture and stone model.

9. Reattachment

Reattach the denture onto its gypsum stone model and press it with the lining jig. Leave undisturbed for 20 minutes or more at room temperature (23°C / 73.4°F).

Note: If the set material is sticky, soak the denture in warm water at 40°C to 50°C (104°F to 122°F) for 5 minutes with the lining jig.

10. Trimming

Remove the denture from the gypsum model. Carefully trim all excess SOFRELINER TOUGH M material from the border areas with a sharp scalpel (See Figure 3).

11. Finishing

For shaping, use the SHAPE ADJUSTMENT POINT (White), by applying light pressure not to exceed 15,000 rpm allowing the point to move in a small circle. For finishing, use the FINISHING POINT (Brown), by applying light pressure not to exceed 4,000 rpm.

Note: Rotate both the SHAPE ADJUSTMENT POINT and the FINISHING POINT from lined area to the denture area so as not to break the margin region (See Figure 4).

Use DIAMOND ROUND BUR (sold separately) or any suitable tool for relief.

■ PATIENT PRECAUTIONS

Patients should be informed of the following instructions to enhance the longevity, durability and safety of a denture lined with SOFRELINER TOUGH M:

1. SOFRELINER TOUGH M lining material should not be scrubbed with a denture brush or toothbrush. The best way to clean SOFRELINER TOUGH M is with a sponge or a soft piece of gauze. While running cold water on the SOFRELINER TOUGH M surface, wipe the surface with sponge or gauze saturated with soap. Use a gentle wiping motion to remove all debris and food deposits from the SOFRELINER TOUGH M lining material. The tooth surface and hard acrylic denture base may be cleaned with a regular denture brush by scrubbing with soap, denture toothpaste or regular denture cleaners at the dentist's discretion.

(gesondert verkauft). Den Kartuschenverschluss der PASTE öffnen. Die Mischspitze auf der Kartusche befestigen, indem Sie die Einkerbungen in Übereinstimmung bringen, die Mischspitze auf die Kartusche drücken und diese 90° im Uhrzeigersinn drehen.

5. Die PASTE aufbringen

Die selbstmischende Paste herausdrücken und gleichmäßig auf den gewebeseitigen Teil der Prothese auftragen. Mit Hilfe eines Spatels wird die Paste gleichmäßig auf alle Flächen verteilt, auf die der PRIMER zuvor aufgebracht wurde.

Hinweis: Falls ein Bereich der zuvor mit Primer benetzten Fläche in dieser Phase nicht mit Paste bedeckt wird, kann die betreffende Stelle beim Einsetzen in den Mund durch Speichel kontaminiert werden. Dadurch kann die die Haftung verringert werden.

6. Einsetzen in den Mund

Saugen Sie überschüssigen Speichel aus dem Mund des Patienten ab. Innerhalb von 1,5 – 2 Minuten nach dem Mischen von SOFRELINER TOUGH M bekommt das Material eine angemessene Zähigkeit. Setzen Sie die Prothese in den Mund des Patienten ein und lassen Sie ihn sehr sanft in zentrischer Okklusion und korrekter vertikaler Dimension zubeißen. Prüfen Sie, ob sich überschüssiges SOFRELINER TOUGH M im Mund des Patienten befindet und entfernen Sie es sofort. Weisen Sie die Patienten darauf hin, dass sie Ihnen sofort mitteilen müssen, falls sie den Eindruck haben, dass SOFRELINER TOUGH M Material in ihren Rachen läuft.

Hinweis: Um Oberkieferprothesen mit SOFRELINER TOUGH M zu unterfüttern, setzen Sie die Prothese von der hinteren Gaumenregion her ein, um das Herabfließen von SOFRELINER TOUGH M Material in den Rachen des Patienten zu vermeiden.

Vermeiden Sie bei der Unterfütterung der Gaumenregion, zuviel Paste auf die zu unterfütternde Oberfläche aufzutragen, und setzen Sie die Prothese so schnell wie möglich in den Mund ein, damit das Material nicht zu zäh wird.

7. Formen des Randbereichs

Ziehen Sie leicht an den Wangen, um den vestibulären Bereich zu formen, während der Patient vorsichtig zubeißt. Falls sich Speichel bildet, diesen absaugen und den Patienten wieder vorsichtig zubeißen lassen. SOFRELINER TOUGH M sollte intraoral mindestens 5 Minuten lang austrocknen.

Hinweis: Falls die Prothese vor Ablauf der 5 Minuten herausgenommen wird, kann dies die Unterfütterung beeinträchtigen.

8. Ausarbeitung

Die Prothese aus dem Mund des Patienten nehmen, mit Wasser spülen und mit dem Luftbläser trocknen. Vorsichtig alles überschüssige SOFRELINER TOUGH M Material mit einem scharfen Skalpell vom Prothesenrand entfernen (siehe Abb. 3).




Abbildung 3




Abbildung 4

9. Endbearbeitung

Verwenden Sie für die Formgebung die Formkorrekturspitze (weiß, SHAPE ADJUSTMENT POINT). Wenden Sie dabei leichten Druck an, Sie sollten jedoch nicht 15.000 rpm überschreiten und erlauben Sie der Spitze kleine Kreisbewegungen. Zum Polieren wird die Endbearbeitungsspitze (braun, FINISHING POINT) unter Anwendung eines leichten Drucks unterhalb von 4.000 rpm verwendet.

Hinweis: Rotieren Sie die Formkorrekturspitze und die Endbearbeitungsspitze von der Unterfütterung zur Prothese, um nicht den Übergangsbereich aufzubrechen (siehe Abb. 4).

Den RUNDEN DIAMANTBOHRER (gesondert verkauft) oder weiteren geeigneten Bohrer für die Korrektur der Innenfläche verwenden.

10. Erneute Anpassung

Die Prothese nach dem im Abschnitt 9 beschriebenen Verfahren erneut anpassen. Falls weiteres Material auf die unterfütterte Oberfläche aufgebracht werden muss, muss die vorhandene Unterfütterung entfernt und durch eine neue ersetzt werden.

11. Entfernung

Schneiden Sie einen großen Teil des SOFRELINER TOUGH M Materials mit einem scharfen Instrument ab. Das verbleibende Material wird durch Fräsen entfernt.

Hinweis: SILICONE REMOVER (gesondert verkauft) entfernt ganz leicht altes Silikonunterfütterungsmaterial von der Prothesenunterlage aus Acryl.

■ KLINISCHE ANWENDUNG DER LABOR- UNTERFÜTTERUNGSMETHODE MIT SOFRELINER TOUGH M

1. Untersuchung des Mundes

Prüfen Sie den intraoralen Zustand durch Untersuchung und Palpation. Untersuchen Sie den Bereich, in dem eine Korrektur der Innenfläche erforderlich ist.

2. Untersuchung der Prothese

Falls die Prothese abgenutzt oder alt ist, muss sie zuerst mit TOKUYAMA REBASE II, einem harten Unterfütterungsmaterial, unterfüttert werden. Das harte Unterfütterungsmaterial sollte in einer angemessenen Schichtdicke aufgetragen werden, damit (wie in Schritt 4 beschrieben) ausreichend Substanz geschaffen wurde. Somit kann SOFRELINER TOUGH M darauf haften.

3. Herstellung eines Gipsmodells

Nehmen Sie einen Abdruck, bei dem der Patient auf die Prothese beifügt. Gießen Sie dann den Abdruck mit Hartgips aus. Fertigen Sie einen Gipschlüssel der Zähne an und montieren Sie die Prothese auf der Unterfütterungsvorrichtung. Blocken Sie das Gipsmodell in dem Bereich mit Wachs aus, in dem evtl. Schmerzen im Mund entstehen könnten. Bringen Sie ein Trennmittel auf den Kieferkamm des Gipsmodells auf, damit das Unterfütterungsmaterial nicht daran haftet.

4. Vorbereitung

Den gewebeseitigen Teil der Prothese mit einem Querhiebbohrer aus Karbid auf die richtige Tiefe fräsen. Die Prothesenränder so abschrägen, dass 1 Millimeter des Materials an den Kanten abgerundet hochragt (siehe Abb. 1). Den Frässtaub mit einem trockenen Pinsel oder einem ölfreien Luftbläser entfernen.

Hinweis: Durch die Verwendung eines runden Bohrs kann auf einfache Weise eine einheitliche Tiefe des Harzes entfernt werden. Der Bohrdurchmesser kann als Hinweis auf die Tiefe der Bohrung dienen.

5. Den PRIMER entnehmen

Die PRIMER-Flasche öffnen. Die Tropfdüse auf der Flasche befestigen. Eine angemessene Menge des PRIMERS in den Kunststoffbecher geben. Die Flasche sofort nach der Entnahme wieder mit dem Deckel fest verschließen.

6. Den PRIMER auftragen

Mit dem PRIMER-Pinsel eine dünne, gleichmäßige Schicht PRIMER dort auf die Prothesenfläche aufbringen, an der diese unterfüttert werden soll. Lassen Sie keine der Stellen aus, auf die der PRIMER aufgetragen werden sollte, da dies zu einer verringerten Haftung führen kann. Trocknete Sie darauffhin die Oberfläche gründlich mit dem Luftbläser bis keine Flüssigkeit mehr zu sehen ist.

7. Die PASTE entnehmen

Die Kartusche mit SOFRELINER TOUGH M PASTE in einen Spender stecken (gesondert verkauft). Den Kartuschenverschluss der PASTE öffnen. Die Mischspitze auf der Kartusche befestigen, indem Sie die Einkerbungen in Übereinstimmung bringen, die Mischspitze auf die Kartusche drücken und diese 90° im Uhrzeigersinn drehen.

8. Die PASTE aufbringen

Die selbstmischende Paste herausdrücken und gleichmäßig auf den gewebeseitigen Teil der Prothese auftragen. Geben Sie die Paste sowohl auf die zu unterfütternde Seite der Prothese als auch auf das Gipsmodell.

9. Erneute Befestigung

Befestigen Sie die Prothese erneut auf den entsprechenden Gipsmodell und drücken Sie sie mit der Unterfütterungsvorrichtung an. Lassen Sie dies mindestens 20 Minuten lang bei Raumtemperatur (23°C / 73,4°F) ruhen.

Hinweis: Falls das ausgehärtete Material klebrig sein sollte, tauchen Sie die Prothese 5 Minuten lang mit der Unterfütterungsvorrichtung in 40°C bis 50°C (104°F zu 122°F) warmes Wasser.

10. Ausarbeitung

Nehmen Sie die Prothese vom Gipsmodell. Vorsichtig alles überschüssige SOFRELINER TOUGH M Material mit einem scharfen Skalpell vom Prothesenrand entfernen (siehe Abb. 3).

11. Endbearbeitung

Verwenden Sie für die Formgebung die Formkorrekturspitze (weiß, SHAPE ADJUSTMENT POINT). Wenden Sie dabei leichten Druck an, Sie sollten jedoch nicht 15.000 rpm überschreiten und erlauben Sie der Spitze kleine Kreisbewegungen. Zum Polieren wird die Endbearbeitungsspitze (braun, FINISHING POINT) unter Anwendung eines leichten Drucks unterhalb von 4.000 rpm verwendet.

Hinweis: Rotieren Sie sowohl die Formkorrekturspitze als auch die Endbearbeitungsspitze von der Unterfütterung zur Prothese, um nicht den Übergangsbereich aufzubrechen (siehe Abb. 4).

Den RUNDEN DIAMANTBOHRER (gesondert verkauft) oder jegliches angemessenes Werkzeug für die Korrektur der Innenflächen verwenden.

■ HINWEISE FÜR DEN PATIENTEN

Die Patienten sollten die folgenden Anweisungen erhalten, um die Langlebigkeit, Halbarkeit und Sicherheit einer mit SOFRELINER TOUGH M unterfütterten Prothese zu erhöhen:

1. SOFRELINER TOUGH M Unterfütterungsmaterial sollte nicht mit einer Prothesen- oder Zahnbürste bearbeitet werden. Am besten wird SOFRELINER TOUGH M mit einem Schwamm oder einer weichen Mullkomresse gereinigt. Die Oberfläche von SOFRELINER TOUGH M unter fließendem kaltem Wasser mit einem eingesiebten Schwamm oder einer eingesiebten Mullkomresse abreiben. Entfernen Sie alle Verschmutzungen und Speisereste mit sanften Wischbewegungen vom SOFRELINER TOUGH M Unterfütterungsmaterial. Die Zahnlücken und die harte Acrylprothesenbasis sollten durch Bürsten mit einer normalen Prothesenbürste mit Seife, Prothesen-Zahnpasta oder einem bilden Prothesenreiniger je nach Ermessen des Zahnarztes gereinigt werden.

2. Die Prothese muss mindestens einmal täglich, vorzugsweise beim Schlafengehen, in einen Prothesenreiniger mit Aktivsauerstoff gelegt werden (z.B. Polident, Efferdent usw.). Die Prothese darf nicht mit einem derartigen Reiniger im Mund des Patienten gesäubert werden. Bei Langzeitanwendung kann, je nachdem, wie gut der Patient seine Prothese pflegt, die Farbe verblasen. Verwenden Sie den Prothesenreiniger im Einklang mit den Anweisungen des Herstellers.

3. Das Eintauchen der Prothese in stark bleichende Lösungen kann die Farbe von SOFRELINER TOUGH M verändern, beeinträchtigt aber nicht dessen Funktion.

4. Wenn die Prothese nicht getragen wird, sollte sie in Wasser aufbewahrt werden.

5. Die unterfütterte Prothese muss alle drei Monate oder wann immer Plaqueablagerungen bemerkt werden vom Zahnarzt untersucht und mit Ultraschall gereinigt werden.

6. SOFRELINER TOUGH M muss regelmäßig auf Beschädigungen hin untersucht werden. Eine Prothese mit veränderten, zerbrochenen, rissigen, losem oder beschädigtem Unterfütterungsmaterial sollte nicht getragen werden. Wird eine beschädigte oder zerbrochene Prothese getragen, kann dies zu Würgereiz, Aspiration, Erstickung oder anderen Beschwerden führen.

7. Bei allen Anzeichen einer Überempfindlichkeit gegen Silikon sollte die Prothese nicht mehr getragen werden und der Patient sollte sofort den Zahnarzt informieren.

WICHTIGER HINWEIS: Der Hersteller von SOFRELINER TOUGH M ist nicht verantwortlich für Schäden oder Verletzungen, die durch unsachgemäße Anwendung dieses Produkts verursacht werden. Es obliegt der persönlichen Verantwortung des Anwenders, die Eignung dieses Produkts für eine entsprechende Anwendung vor dem Gebrauch sicherzustellen.

Die Produktspezifikationen von SOFRELINER TOUGH M können ohne Vorankündigung geändert werden. Bei Änderungen der Produktspezifikationen können sich die Anweisungen und Vorsichtsmaßnahmen ebenfalls ändern.

■ NEDERLANDS

Lees alle instructies zorgvuldig door alvorens SOFRELINER TOUGH M te gebruiken.

■ PRODUCTBESCHRIJVING EN ALGEMENE INFORMATIE

1. SOFRELINER TOUGH M is een voeringsmateriaal van additieve silicone voor uitneembare gebitsprothesen voor gebruik aan de stoel. SOFRELINER TOUGH M is conform ISO 10139-2 "Zachte voeringsmaterialen voor prothesen Deel 2: Materialen voor lageduur toegepasten".

2. De SOFRELINER TOUGH M kit bevat pasta [PASTE], primer [PRIMER] en andere bijbehorende onderdelen zoals mengtip, tuit, druppelbekertjes, kwastjes, uitwerk tip (witte, SHAPE ADJUSTMENT POINT), afwerk tip (bruin, FINISHING POINT).

3. De primer [PRIMER] wordt alleen gebruikt voor bonding van acryl oppervlakken, niet om nylon, metalen en siliconen oppervlakken te bonden. De pasta [PASTE] wordt geleverd in een automix cartridge applicatiesysteem. Het materiaal verhardt in 5 minuten in de mond of in 20 minuten bij kamertemperatuur (23°C / 73,4°F) en is geur- en smaakloos.

4. Als er een breuk is in de afgewerkte voering, de voering volledig verwijderen en de procedure herhalen.

5. Gebruik de volgende instrumenten voor aanpassen van de vorm en afwerking.

Fases	Instrument	Vorm
Bijwerken	Scherp scalpel	Iets rond mes
Vormen	Uitwerk tip (witte, SHAPE ADJUSTMENT POINT)	Rond afgeschuind eind
Afwerken	Afwerk tip (bruin, FINISHING POINT)	Rond afgeschuind eind
Relief	Ronde diamantboor (apart verkocht)	Rond

6. Gebruik de volgende instrumenten voor aanpassen van de vorm en afwerking.

Fases	Instrument	Vorm
Bijwerken	Scherp scalpel	Iets rond mes
Vormen	Uitwerk tip (witte, SHAPE ADJUSTMENT POINT)	Rond afgeschuind eind
Afwerken	Afwerk tip (bruin, FINISHING POINT)	Rond afgeschuind eind
Relief	Ronde diamantboor (apart verkocht)	Rond

7. Gebruik de volgende instrumenten voor aanpassen van de vorm en afwerking.

Fases	Instrument	Vorm
Bijwerken	Scherp scalpel	Iets rond mes
Vormen	Uitwerk tip (witte, SHAPE ADJUSTMENT POINT)	Rond afgeschuind eind
Afwerken	Afwerk tip (bruin, FINISHING POINT)	Rond afgeschuind eind
Relief	Ronde diamantboor (apart verkocht)	Rond

8. Gebruik de volgende instrumenten voor aanpassen van de vorm en afwerking.

Fases	Instrument	Vorm
Bijwerken	Scherp scalpel	Iets rond mes
Vormen	Uitwerk tip (witte, SHAPE ADJUSTMENT POINT)	Rond afgeschuind eind
Afwerken	Afwerk tip (bruin, FINISHING POINT)	Rond afgeschuind eind
Relief	Ronde diamantboor (apart verk	